

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application.

**Listing of Claims:**

1. (Original) 1. A method for forming homogeneous mixture of powders of organic materials including at least one dopant component and one host component to provide a homogeneous mixture for forming a pellet for thermal physical vapor deposition producing an organic layer on a substrate for use in an organic light-emitting device, comprising:
  - a) combining organic materials, such materials including at least one dopant component and one host component;
  - b) providing a liquid to emulsify the organic materials;
  - c) mixing the emulsified organic materials in a container to form a homogeneous mixture of organic material;
  - d) heating the organic materials in a container until the liquid is evaporated and a solidified homogeneous mixture of organic materials remain;
  - e) removing the solidified homogeneous mixture of organic materials from the container;
  - f) pulverizing the solidified mixture of organic materials into a homogeneous mixture of organic powder; and
  - g) compacting the homogenous mixture of organic powder, to form a pellet suitable for thermal physical vaporization to produce an organic layer on a substrate for use in an organic light-emitting device.
2. (Original) The method of claim 1 wherein the amount of dopant component varies between 0.1 and 20% by weight of the total weight of the mixture.
3. (Original) The method of claim 1 wherein the compaction of the homogeneous mixture of organic powder to form a pellet is compacted in a range of pressures between 3,000 and 20,000 pounds per square inch.
4. (Original) The method of claim 1 wherein the container is formed from glass or metal.
5. (Original) The method of claim 1, wherein the container includes high temperature metals Ta, W or Pt.

6. (Original) The method of claim 1, wherein the mixing includes using a ball mill, high-speed propeller, turbine blade or ultrasonication.

7. (Original) The method of claim 6, wherein the ultrasonication includes an ultrasonic horn, which operates in a range of frequencies between 10-30 kHz.